

	Standard – Test Method	Unit	Result	
			Wax	Varnish
DIMENSIONS	EN 427	mm	600 ± 0.5% 300 ± 0.5%	
SQUARENESS	EN 427	mm	600: < 1.0mm 300: < 0.5mm	
THICKNESS	ISO 7322	mm	3.0 ± 0.3%	
APPARENT DENSITY	EN 672	Kg/m ³	≥ 200	
DIMENSION STABILITY	EN 434	%	≤ 0.4	
CURLING	EN 434	mm	≤ 6	
MOISTURE CONTENT	EN 12105	%	≤ 7	
FORMALDEHYDE	EN 12149, method C	mg/Kg	≤ 95	
VINYL CHLORIDE MONOMER (VCM)	EN 12149, TEST B	mg/Kg	≤ 0,2	
THERMAL RESISTANCE	EN 12667	m ² K/w	0.0583	0.0572
REACTION TO FIRE	EN 15102:2007	Class	E	E
SOUND ABSORPTION	ISO 354	α _w	0.10	
RELEASE OF HEAVY METALS AND SPECIFIC ELEMENTS	EN 12149		fulfilled	